

Premium III Pak-Free Asphalt

A Quality Controlled, Low Odor, Hot-Melt Adhesive Packaged in Meltable Plastic Film

FEATURES

- Consumable packaging
- Quality controlled product
- UL & FM Approved

BENEFITS

- Less packaging waste
- Consistent performance values
- Fire/wind protection

DESCRIPTION

Premium III Pak-Free Asphalt is a high quality roof mopping asphalt processed from a closely monitored asphalt flux, and packaged in easy to handle polyethylene plastic wrappers. The wrapping plastic on each package is suitable for placement in a standard roofing hot-kettle without removing it from the asphalt. In addition, a compatible low odor additive is blended within the hot melt to reduce jobsite odors. Premium III Pak-Free Asphalt meets tightly controlled performance characteristics and performs in accordance with ASTM D 312, the Standard Specification for Asphalt Used in Roofing.

BASIC USES

Premium III Pak-Free Asphalt is designed for application as a thermoplastic hot melt adhesive in a variety of built-up roof configurations. The Pak-Free packaging helps reduce jobsite waste by eliminating asphalt keg containers and increasing the amount of asphalt which may be shipped per pallet. The meltable polyethylene wrapper is not removed from each asphalt package, instead, is placed in the hot kettle as a unit and melts away.

Premium III Pak-Free Asphalt is suitable for use as an interply adhesive for standard built up roofs, especially for low and steep-sloped roof applications. In addition, Premium III Pak-Free Asphalt may be used as a flood coat surfacing adhesive for asphalt built up and SBS modified bitumen roof systems, along with being recommended for use to adhere Tremco approved roof insulation boards and base sheets to acceptable substrates.

PACKAGING

Available in 50 lb (22.5 kg) units, individually wrapped in a meltable polyethylene film. Sold by the pallet only.

Two pallet sizes are offered. Pallet size is based on regional availability.

- 2,500 lbs (1,134 kg) per pallet - 50 units
- 2,000 lbs (907 kg) per pallet - 40 units

APPLICATION

General Application Data: Roof replacement usually involves more complexities than new construction roofing. Often encountered are situations such as rusted/deteriorated decks, rotted wood components, and rooftop equipment which cannot be moved or shut down, and numerous other conditions.

The following application information is designed to serve as a general guide. Your local Tremco Representative will prepare detailed specifications based upon your roof's conditions.

Structural Deck: Must be properly designed and structurally sound.

Drainage: Ponding conditions are unacceptable and will adversely affect performance of any roofing system. If positive drainage does not exist, water removal must be facilitated by lowering drains, and/or installing additional drains, tapered insulation, or an approved cellular concrete slope system.

Premium III Pak-Free Asphalt

APPLICATION

CONTINUED

Insulation: Insulation must be dry and kept dry. No more insulation shall be installed than can be covered that day.

Acceptable Insulations:

TYPE	MINIMUM THICKNESS*	FACER
Fiberboard	1/2" (13mm)	Coated
Perlite	1" (25mm)	None

SUBLAYER

Fiberboard	1/2" (13mm)	None
Perlite	1" (25mm)	None
Isocyanurate	1" (25mm)	Black/Gray

Maximum size: 4' x 8' (1219mm x 2438mm)

* Minimum thickness for application of Premium III. Follow insulation manufacturer's instructions to obtain minimum thickness for spanning metal deck ribs.

Installation Procedures: According to particular project specifications, prepare surface to be covered:

- Replace areas of wet insulation, deteriorated deck, and wood components.
- Install roof insulation or base sheet by mechanical attachment or in a uniform and continuous mopping of Premium III applied at 25-30lb/100 ft² (1.2 - 1.4 kg/m²).

Plan placement of roofing ply sheets to ensure that water will flow over or along, but not against exposed edges. Use standard kettle equipped with circulating pump. Do not heat Premium III above a maximum kettle temperature of 550°F (288°C). Starting at low point of roof, apply a uniform continuous mopping of Premium III using standard roofing mop or Tremco approved felt layer.

Use ply sheets to start and finish roof membrane along edges, terminations and projections as specified. Install ply sheets, overlapping each previous ply the specified width. Embed each ply in uniform and continuous mopping of Premium III asphalt, applied within its Equiviscous Temperature (EVT) range.

Interply application rate:	FELT	LB/100 FT ² *
	BURmastic Glass Ply	25 (1.2 kg/m ²)
	Burmastic Composite Ply	25 (1.2 kg/m ²)
	PolyTHERM	25 (1.2 kg/m ²)
	THERMglass	25 (1.2 kg/m ²)
	POWERply MB systems (all plies)	25 (1.2 kg/m ²)

* Application Tolerance: +20%

Ply shall never touch ply. Apply Premium III Pak-Free Asphalt no more than ten feet ahead of each roll. Lightly broom plies from unmopped side to assure complete adhesion. Tie in previous work 24" (600mm). Lap ply sheet ends 6" (150mm). Stagger end laps. Avoid walking on plies until Premium III Pak-Free Asphalt has cooled. Install flashings as specified.

Gravel: Apply Premium III Pak-Free Asphalt over roof surface at 60 lb/100 ft² (2.9 kg/m²) + 20%. Immediately broadcast 400 lb/100 ft² (19.5 kg/m²) of new, clean gravel or 300 lb/100 ft² (14.5 kg/m²) of slag into adhesive. Aggregate shall conform to ASTM D 1863.

Smooth Surface: Consult your local Tremco Representative for specific applications suitable for your geographic area.

Premium III Pak-Free Asphalt quantities for waterstop/tieoffs, flashings, miscellaneous detail applications and minimum kettle capacity are not included in inter-ply and flood coat application rates.

- Not intended to perform under ponding conditions. Positive drainage required.
- Not to be exposed to solvents, oils, or other contaminants harmful to asphaltic materials.

SURFACING OPTIONS

APPLICATION RATE

Premium III Pak-Free Asphalt

LIMITATIONS

- Not for use over expanded polystyrene (EPS) or EPS composite insulations installed in any configuration unless EPS is encapsulated within lightweight insulating cellular concrete.
- Not for hot applying membrane systems directly over isocyanurate insulation. Isocyanurate insulations must be overlaid with either 1/2" (13mm) fiberboard, 3/4" (19mm) fibrous glass, or 1"(25mm) perlite (minimum thicknesses).
- Not for use over phenolic insulations installed in any configuration.
- Backnail felts on roofs with slopes 2:12 (2" per foot) or greater. Do not install on roofs with slopes greater than 3:12 (3" per foot).
- Do not install when ambient temperatures are below 50°F (10°C) unless special cold weather application procedures are followed. Consult your local Tremco Representative for details.
- Do not exceed a maximum kettle temperature of 550°F (288°C)

PHYSICAL PROPERTIES

PROPERTY	TYPICAL VALUE	TEST METHOD
Softening Point	195 - 205°F (90.5 - 96°C)	ASTM D 36
Penetration @ 77°F	15 - 30 dmm	ASTM D 5
Flash Point, min	575°F (302°C)	ASTM D92
Ductility @ 77°F	2.5 cm	ASTM D113
EVT (125 cP)	400-450°F (204 - 221°C)	ASTM 4402

PRECAUTIONS

Users must read container labels and Safety Data Sheets for health and safety precautions prior to use.

MAINTENANCE

Your local Tremco Roofing Representative can provide you with effective maintenance procedures which may vary, depending upon specific conditions. Periodic inspections, early repairs and preventative maintenance are all part of a sound roof program.

TECHNICAL SUPPORT

Your local Tremco Representative, working with the Technical Service Staff, can help analyze conditions and needs to develop recommendations for special applications. The services of the Tremco Research Center, which has earned a unique reputation in weatherproofing technology, complement and extend the service of the Tremco Service Staff.



Roofing & Building Maintenance

3735 Green Road
Beachwood, Ohio 44122

220 Wicksteed Avenue
Toronto, Ontario, M4H 1G7

www.tremcoroofing.com

1.800.852.6013

Tremco Roofing and Building
Maintenance is part of Tremco
Construction Products Group.

Tremco is a US Registered trademark of Tremco CPG Inc.

The information provided on this data page supersedes all previous data concerning this product and its application.

The Statements provided concerning the materials shown are intended solely as a general guide for material usage and are believed to be true and accurate. Since the manner of use is beyond our control, Tremco DOES NOT MAKE NOR DOES IT AUTHORIZE ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR ANY PURPOSE, OR ANY OTHER WARRANTY, GUARANTEE OR REPRESENTATION, EXPRESSED OR IMPLIED, CONCERNING THIS MATERIAL EXCEPT THAT IT CONFORMS TO TREMCO'S PRODUCT SAMPLE. Buyer and user accept the product under those conditions and assume the risk of any failure, injury of person or property and loss or liability resulting from the handling, storage or use of the product, whether or not it is handled, stored, used in accordance with directions or specifications. UNDER NO CIRCUMSTANCE SHALL TREMCO BE LIABLE FOR CONSEQUENTIAL OR INCIDENTAL DAMAGES ARISING FROM ANY BREACH OF WARRANTY. IN ALL CASES, TREMCO'S LIABILITY IS LIMITED, AT TREMCO'S OPTION, TO THE REPLACEMENT OF GOODS, OR THEIR VALUE, PROVEN TO BE DEFECTIVE IN MANUFACTURING.