

# AlphaGrade™ Top Coat

## High Performance, Two-Component, Bio-Based, Polyurethane Top Coat

### FEATURES

Bio Content

Virtually Odorless

High Solids

Low VOC

Highly Reflective (White)

### BENEFITS

- Rapidly renewable content makes product sustainable and environmentally responsible
- System is perfect for sensitive accounts such as schools, hospitals, occupied buildings, etc.
- Results in thicker dry film vs. lower solids products
- 0 g/L
- Lowers rooftop temperatures resulting in less stress and potential energy savings

### DESCRIPTION

AlphaGrade Top Coat is a two-component, bio-based, polyurethane liquid applied product.

### BASIC USES

AlphaGrade Top Coat is used as the surfacing coat for the AlphaGrade system in conjunction with AlphaGrade and AlphaGrade Base Coat products.

### PACKAGING

**Pails:** 2.5 gal (7.5 L) Kits

Part A - 2 gals (7.5 L) packaged in a 5 gal (18.9 L) container

Part B - 0.5 gal (1.8 L)

**Drums:** 250 gal (946.3 L) Kits

Part A - 4 drums total - Each containing 50 gals (189.2 L) packaged in a 55 gal (208.1 L) container

Part B - 1 drum total - Containing 50 gals (189.2 L) packaged in a 55 gal (208.1 L) container

### COLOR

White

### GRADE

Brush, Roller, Spray, Squeegee & Backroll

### POT LIFE

20-25 minutes, 77°F (25°C)/50% RH.

*\*Temperature dependent - Increasing temperature reduces expected pot-life*

### STORAGE

12 months shelf life in unopened containers when properly stored.

#### DO NOT FREEZE PART B

Recommended storage conditions are indoors in a ventilated, dry area removed from heat, open flame, ignition sources, and direct sunlight. Storage temperatures should range from 60-70°F (15-21°C) and must not drop below 32°F (0°C) or exceed 110°F (43°C).

On the job site, materials should remain on the pallet until use and be stored in a shaded, ventilated area. Materials should be covered with a light-colored, reflective tarp for protection against the elements. Allow for adequate air flow inside the pallets.

Shelf life could be affected if the product is not stored properly.

### APPLICATION

**Preparation:** AlphaGrade Base Coat or Top Coat surface must be cured, clean, dry, in sound condition, and free of dirt, debris, and contaminants prior to application.

#### Mixing:

Product material temperatures must be above 45°F (7°C) when mixing.

**Pails:** Use a heavy duty power drill with Jiffy Mixer attachment. Cordless drills are not recommended and may not properly mix the materials.

Mix Part A for 1 minute before adding Part B. After adding Part B mix the combined

# AlphaGrade™ Top Coat

## APPLICATION CONTINUED

materials for a minimum of 2 minutes moving the mix blade from top to bottom. Make sure to mix areas around side walls and bottom of pail. Improper mixing will result in non-curing material.

**Drums:** Use industrial drum mixing equipment to mechanically mix each Part A and Part B container. Mix until product is consistent in appearance and viscosity. Do not thin.

**Do not break down kits into smaller quantities -MIX ENTIRE KIT.**

**Priming:** AlphaGrade Base and Top Coats should be top-coated within 72 hours of application. If cured base or top coat is exposed for longer than 72 hours, an application of Tremco BIO Prime will be required to promote adhesion between coats.

**Installation:** Install product using one of the approved application methods evenly at the recommended coverage rate. Grid roof and use wet mil gauges to monitor coverage rates throughout application. Never fully invert empty pails in an attempt to drain material as this may result in improperly cured material during application.

**Non-Skid Application:** Install an additional layer of white top coat at 1-1½ gal / 100 sq. ft. (16-24 wet mils) (0.4-0.6 L/m<sup>2</sup>) and immediately broadcast and backroll an approved non-skid media. Color striping can be installed in 3-4" wide areas along the perimeter of the walkway area at a coverage rate of 1-1½ gal / 100 sq. ft. (16-24 wet mils) (0.4-0.6 L/m<sup>2</sup>) to provide identification of the areas on the roof.

**Approved Non-Skid Media:**

- Silica Sand (20-40 mesh) - Coverage: 20-30 lbs. / 100 sq. ft.
- No. 11 Roofing Granule - Coverage: 10-15 lbs. / 100 sq. ft.

## COVERAGE RATES

**Top Coat:** 2 gals / SQ (0.8 L/m<sup>2</sup>) (32 wet mils)

**Non-Skid Coat:** 1-1.5 gals / SQ (0.4-0.6 L/m<sup>2</sup>) (16-24 wet mils)

Coverage rates are listed at minimum recommended rates. The application surface can affect the necessary coverage rate.

## TEMPERATURE RECOMMENDATIONS

**Min Ambient:** 45°F (7.2°C)

**Max Ambient:** 110°F (43.3°C)

- Minimum temperatures must be rising following application
- Do not apply when dew point is within 5°F (2.77°C) of ambient temperatures
- Do not apply when precipitation, fog or dew is imminent prior to cure of the product

## CURE TIMES

**Skin Time:** 3-4 hours @ 77°F (25°C) / 50% RH

**Recoat Time:** 6-7 hours @ 77°F (25°C) / 50% RH

*Note: Cure times can be effected by a number of weather and jobsite conditions including but not limited to exposure to sunlight and wind, humidity, precipitation, and temperature.*

## ACCEPTABLE ROOF SURFACES

Gravel-Surfaced Built-Up Roofs

## SPRAY EQUIPMENT RECOMMENDATIONS

**GENERAL GUIDELINES**

**Component:** Two-Component

**Pressure:** 4,500 psi

**Ration (Part A : Part B):** 4:1

**Tip Size:** .045 - .055

**Filters:** Remove

**Hose Type:** High Pressure

**WHIP:** ¼" High Pressure

**Product Temp:** Ambient

- Must use heavy duty or industrial grade spray tips
- Properly clean and maintain spray equipment before, during and after use
- Equipment should be properly grounded during use

## CLEAN UP

Before the product cures, clean surfaces and equipment with Isopropyl Alcohol. Spray equipment can be flushed/cleaned using MEK or xylene.

# AlphaGrade™ Top Coat

## LIMITATIONS

- Not recommended for use over the following:

**Roof Decks:** Direct applications to cementitious wood fiber, metal, poured-in-place gypsum, structural lightweight or lightweight insulating concrete, and wood decks (includes plywood, tongue and groove, etc.).

**Products/Systems:** Clay tile, expanded or extruded polystyrene insulation, fluoropolymer finished metal, shingles, silicone-based products, and tar-based products.

- Not for use under continuous immersion

## PHYSICAL PROPERTIES

PHYSICAL PROPERTY	TEST METHOD	VALUE
Accelerated Weathering	ASTM D5147	Pass
Dynamic Puncture Resistance	ASTM D5635	32.5 J
Elongation	ASTM D412	130%
Low Temperature Crack Bridging	ASTM C836	Pass
Low Temperature Flexibility	ASTM D5147	Pass @ -55°F
Static Puncture Resistance	ASTM D5602	20 lbf
Tear Strength	ASTM D624	36 lbf/in
Tensile Strength	ASTM D412	274 psi
Water Absorption	ASTM D95	1.0%
Volume Solids	ASTM D2697	100%
Weight Solids	ASTM D1644	100%

## CODES & APPROVALS



## MAINTENANCE

Your local Tremco Roofing sales representative can provide you with effective maintenance procedures which may vary, depending upon specific conditions. Periodic inspections, early repairs and preventative maintenance are all part of a sound roof program.

## PRECAUTIONS

Users must read container labels and Safety Data Sheets for health and safety precautions prior to use.

## TECHNICAL SUPPORT

Your local Tremco Roofing sales representative, working with the Technical Service Staff, can help analyze conditions and needs to develop recommendations for special applications.



[www.tremcoroofing.com](http://www.tremcoroofing.com)  
3735 Green Road  
Beachwood, Ohio 44122  
1.800.852.6013

220 Wicksteed Avenue  
Toronto, Ontario M4H 1G7  
1.800.668.9879

Tremco Roofing & Building  
Maintenance is part of Tremco  
Construction Products Group

Tremco is a US Registered trademark of Tremco CPG Inc.

The information provided on this data page supersedes all previous data concerning this product and its application.

The Statements provided concerning the materials shown are intended solely as a general guide for material usage and are believed to be true and accurate. Since the manner of use is beyond our control, Tremco DOES NOT MAKE NOR DOES IT AUTHORIZE ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR ANY PURPOSE, OR ANY OTHER WARRANTY, GUARANTEE OR REPRESENTATION, EXPRESSED OR IMPLIED, CONCERNING THIS MATERIAL EXCEPT THAT IT CONFORMS TO TREMCO'S PRODUCT SAMPLE. Buyer and user accept the product under those conditions and assume the risk of any failure, injury to person or property and loss or liability resulting from the handling, storage or use of the product, whether or not it is handled, stored, used in accordance with directions or specifications. UNDER NO CIRCUMSTANCE SHALL TREMCO BE LIABLE FOR CONSEQUENTIAL OR INCIDENTAL DAMAGES ARISING FROM ANY BREACH OF WARRANTY. IN ALL CASES, TREMCO'S LIABILITY IS LIMITED, AT TREMCO'S OPTION, TO THE REPLACEMENT OF GOODS, OR THEIR VALUE, PROVEN TO BE DEFECTIVE IN MANUFACTURING.